



PC-ABS (polycarbonate-ABS) is one of the most widely used industrial thermoplastics. PC-ABS offers the most desirable properties of both materials - the superior mechanical properties and heat resistance of PC and the excellent features of ABS. PC-ABS blends are commonly used in automotive, electronics and telecommunications applications. Additionally, a PC-ABS part manufactured on a FDM mc™ series system is 5-60 percent stronger than a part made on previous FDM systems. When combined with a Stratasys FDM system, PC-ABS gives you Real Parts™ for conceptual prototyping, design verification, and direct digital manufacturing.

| Mechanical Properties ¹ | Test Method | Imperial | Metric |
|--|-------------|--------------|-----------|
| Tensile Strength (Type 1, 2"/min) | ASTM D638 | 5,900 psi | 41 MPa |
| Tensile Modulus | ASTM D638 | 278,000 psi | 1,917 MPa |
| Tensile Elongation | ASTM D638 | 6% | 6% |
| Flexural Strength (Method 1, 0.05"/min) | ASTM D790 | 9,800 psi | 68 MPa |
| Flexural Modulus | ASTM D790 | 280,000 psi | 1,931 MPa |
| Flexural Elongation | ASTM D790 | 70% | 70% |
| IZOD Impact, notched (Method A, 23°C) | ASTM D256 | 3.7 ft-lb/in | 196 J/m |
| IZOD Impact, un-notched (Method A, 23°C) | ASTM D256 | 9 ft-lb/in | 481 J/m |

| Thermal Properties ³ | Test Method | Imperial | Metric |
|-------------------------------------|-------------|-----------------------------|-----------------------------|
| Heat Deflection Temp (HDT), 66 psi | ASTM D648 | 230°F | 110°C |
| Heat Deflection Temp (HDT), 264 psi | ASTM D648 | 205°F | 96°C |
| Vicat Softening | ASTM D1525 | 234°F | 112°C |
| Coefficient of Thermal Expansion | ----- | 4.10E-5 in/in F | ----- |
| Glass Transition Temp (Tg) | DMA (SSYS) | 257°F | 125°C |
| Melt Point | ----- | Not Applicable ² | Not Applicable ² |

| Other ³ | Test Method | Value |
|------------------------|-------------|---------------------------|
| Specific Gravity | ASTM D792 | 1.20 |
| Density | ASTM D792 | 0.0397 lb/in ³ |
| UL 94 Flame Class | UL94 | HB 0.85mm |
| Rockwell Hardness | ASTM D785 | R110 |
| Dielectric S (kV/mm) | IEC 60112 | 35.0 |
| Dielectric C (@100 Hz) | IEC 60250 | 3.1 |
| Dielectric C (@1 Mhz) | IEC 60250 | 3.0 |

► See reverse for system availability.

The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Tested parts were built on FDM 400mc @ 0.10" (0.254 mm) slice. Product specifications are subject to change without notice.

¹ Build orientation is on side long edge. ² Due to amorphous nature, material does not display a melting point. ³ Literature value unless otherwise noted.

| System Availability | Layer Thickness Capability | Support Structure | Color |
|------------------------|--|-------------------|---------|
| FDM 360mc FDM 400mc | 0.013 inch (0.330 mm) 0.010 inch (0.254 mm) 0.007 inch (0.178 mm) 0.005 inch (0.127 mm) | Soluble Supports | ■ Black |

For more information about Stratasys systems and materials, contact your representative at +1 888.480.3548 or visit www.stratasys.com

Stratasys Inc.
7665 Commerce Way
Eden Prairie, MN 55344-2080
+1 888 480 3548 (US Toll Free)
+1 952 937 3000 (Main)
+1 952 937 0070 (Fax)
www.stratasys.com
info@stratasys.com

Stratasys GmbH
Weismüllerstrasse 27
60314 Frankfurt am Main
Germany
+49 69 420 9943 0 (Tel)
+49 69 420 9943 33 (Fax)
europe@stratasys.com